Issued: 2019/09/05
New : 2024/10/11

NAN YA PLASTICS CORPORATION
ELECTRONIC MATERIALS DIVISION.
COPPER CLAD LAMINATE DEPARTMENT
NO. 390 SEC 6 NANJING E RD, NEIHU DISTRICT, TAIPEI, TAIWAN

Glass cloth base modified resin
Flame retardant copper clad laminate

NP-530

■ FEATURES

- Low dielectric constant and low dissipation factor at high frequency range
- Greater design flexibility by allowing the same impedance
- Suit for Antenna、Base station、PA and LNB application
- Excellent dimensional stability

■ PERFORMANCE LIST

Characteristics		Unit	Conditioning	Typical Values	SPEC	Test Method
Permittivity	Process	-	10GHz/23℃	3.08	-	2.5.5.5
	Design	-	-	2.98		Differential phase length
Loss Tangent		-	10GHz/23℃	0.0030	-	2.5.5.5
				0.0029		SPDR
Volume resistivity		MΩ-cm	C-96/35/90	$4x\ 10^8$~$5x\ 10^9$	10^6↑	2.5.17
Surface resistivity		MΩ	C-96/35/90	$5x\ 10^7$~$5x\ 10^8$	10^4↑	2.5.17
Arc resistance		SEC	D-48/50+D-0.5/23	120↑	60 ↑	2.5.1
Dielectric breakdown		KV	D-48/50	60 ↑	40 ↑	2.5.6
Moisture absorption		%	D-24/23	0.01~0.02	0.35 ↓	2.6.2.1
Flammability		-	C-48/23/50	94V0	94V0	UL94
Peel strength 1 oz		lb/in	288℃x10" solder floating	6~8	-	2.4.8
Thermal stress		SEC	288℃ dipping	300 ↑	10 ↑	2.4.13.1
Pressure cooker 2 hr (2 atm 121℃)		SEC	288℃ dipping	300 ↑	N/A	-
Dimensional stability X-Y axis		%	E-0.5/170	0.010-0.030	0.050 ↓	2.4.39
Coefficient of thermal expansion Z-axis before Tg		ppm/℃	TMA	20-30	N/A	2.4.24
Glass transition temp		℃	DMA	230	N/A	2.4.25
Td (5% weight loss)		℃	TGA, 10℃/min	420	325 ↑	-

Data shown are nominal values for reference only.

NOTE:
The average value in the table refers to samples of .0307" 1/1.
Test method per IPC-TM-650

■ PRODUCT SIZE & THICKNESS

THICKNESS INCH (mm)	**THICKNESS TOLERANCE**	COPPER CLADDING OZ (μm)	SIZE INCH	SIZE mm
0.0057"(0.145)	±0.0007"(0.018)	0.5 (17) HTE,RTF 1.0 (35) HTE,RTF	49 x 37 49 x 41.1 49 x 43	1245 x 0940 1245 x 1045 1245 x 1092
0.0107"(0.272)	±0.0010"(0.025)			
0.0207"(0.529)	±0.0020"(0.050)			
0.0307"(0.780)	±0.0020"(0.050)			
0.0407"(1.034)	±0.0030"(0.076)			
0.0607"(1.542)	±0.0030"(0.076)			

＊Use resin coating copper, need to plasma after desmear process.